

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 455 401 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
17.07.1996 Bulletin 1996/29

(51) Int Cl.⁶: **C09K 11/02, C09K 11/61,
C09K 11/58, C09K 11/57,
C09K 11/56**

(21) Application number: **91303636.4**

(22) Date of filing: **23.04.1991**

(54) **Encapsulated electroluminescent phosphor and method for making same**

Eingekapselter elektrolumineszenter Phosphor und Verfahren zur Herstellung desselben

Phosphore électroluminescent encapsulé et méthode pour sa fabrication

(84) Designated Contracting States:
DE FR GB IT NL SE

(30) Priority: **25.04.1990 US 514440**

(43) Date of publication of application:
06.11.1991 Bulletin 1991/45

(73) Proprietor: **MINNESOTA MINING AND
MANUFACTURING COMPANY**
St. Paul, Minnesota 55133-3427 (US)

(72) Inventor: **Kenton, D. Budd**
c/o Minnesota Mining and
St. Paul, Minnesota 55133-3427 (US)

(74) Representative: **Baillie, Iain Cameron et al**
c/o Ladas & Parry
52-54 High Holborn
London WC1V 6RR (GB)

(56) References cited:
EP-A- 0 160 856 WO-A-91/10715
US-A- 4 999 219

- **PATENT ABSTRACTS OF JAPAN, vol. 14, no. 57**
(C-684), 2 February 1990; & JP-A-12 84 583

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 455 401 B1

Description

Field of Invention

5 The present invention relates to electroluminescent phosphor particles, particularly encapsulated phosphor particles which exhibit strong moisture resistance and high electroluminescent brightness. The present invention also relates to a method for making such encapsulated phosphor particles.

Background

10 Phosphor particles are used in a variety of applications such as flat panel displays and decorations, cathode ray tubes, and fluorescent lighting fixtures. Luminescence or light emission by phosphor particles may be stimulated by application of heat (thermoluminescence), light (photoluminescence), high energy radiation (e.g., x-rays or e-beams), or electric fields (electroluminescence).

15 Electroluminescent ("EL") phosphors are of particular commercial importance. The luminescent brightness and "maintenance" of such brightness of such phosphors are two important criteria for characterizing phosphor particles. Luminescent brightness is typically reported as a quantity of light emitted by the subject phosphor when excited. When reported in absolute brightness, e.g., in foot-Lamberts ("ft-L") or cd/m^2 , the conditions under which the phosphor is excited should also be reported as the absolute luminescent brightness of a given phosphor typically depends upon a
20 combination of several factors. For instance, the absolute brightness of an electroluminescent phosphor should be reported with specified voltage and frequency of the applied electric field and temperature of the phosphor. The luminescent brightness attained is also dependent in part upon the physical characteristics and specifications of the test device used to measure the magnitude of emitted light. A typical test device possesses many of the same members as the thick film electroluminescent devices discussed below. With regard to accurately determining the absolute bright-
25 ness of a subject phosphor, important characteristics thereof include the thickness of the phosphor layer, the concentration or loading of the phosphor particles in the dielectric matrix, the characteristics of the particular dielectric matrix material, and the transparency of the front electrode. Because of the sensitivity of phosphor emission brightness to varying conditions of excitement, the brightness of phosphors are more typically reported as relative brightnesses rather than as absolute brightness. "Maintenance" refers to the rate at which phosphors lose brightness during oper-
30 ation. As discussed by Thornton in Electroluminescent Maintenance, Jour. of Electrochem. Soc., pp 895-907, Vol. 107, No. 11, Nov. 1960, such a decrease in brightness with operating time is a typical characteristic of phosphors. Furthermore, the rate of decay is substantially increased if the phosphor particles are subjected to conditions of high humidity while being operated. "Atmospheric water vapor is perhaps the most important adverse influence on electroluminescence maintenance from the point of view of practical application." Ibid. This effect of moisture or high humidity is referred to herein as "humidity-accelerated decay".

35 Decay characteristics observed during operation at zero relative humidity are referred to as the intrinsic maintenance characteristics or intrinsic decay of the subject phosphor. The intrinsic decay varies with operating conditions such as voltage, frequency, and temperature, but is essentially reproducible for a given phosphor for a given set of operating conditions. As noted by Thornton, operation in high humidity, e.g., relative humidity of greater than about 80
40 percent can increase the decay rate by a factor of 10 or more with respect to the subject phosphor's intrinsic decay.

Particulate EL phosphors are most commonly used in thick film constructions. These devices typically include a layer of an organic dielectric matrix, e.g., polyester, polyethylene terephthalate, cellulosic materials, etc., preferably having a high dielectric constant, loaded with phosphor particles, e.g., sulfide-based phosphor particles. Such layers are typically coated on a plastic substrate having a transparent front electrode. A rear electrode, e.g., an aluminum foil
45 or screen printed silver ink, is typically applied to the back side of the phosphor layer. When an electric field is applied across the electrodes, the proximate portions of the layer emit light as the phosphor particles therein are excited. Such constructions may further comprise optional dielectric layers between the phosphor layer and rear electrodes.

Organic matrices and coatings can temporarily delay or slow the rate of humidity-accelerated decay, however, after moisture permeates the matrix or coating, rapid loss of luminescent brightness is typically exhibited. Organic
50 matrices and substrate materials have typically been insufficiently effective in preventing diffusion of water vapor to the phosphor particles, and have accordingly been ineffective in preventing subsequent decay of brightness. For this reason, thick film electroluminescent devices are typically encased in relatively thick, e.g., 25 to 125 microns, envelopes of moisture-resistant materials such as fluorochlorocarbon polymers such as ACLAR Polymers from Allied Chemical. Some of the problems with such envelopes include typically substantial expense, unlit borders, and potential for delam-
55 ination, e.g., under heat.

U.S. Patent No. 4,097,776 (Allinikov) discloses electroluminescent phosphors coated with a liquid crystal in a solution-based technique. U.S. Patent No. 4,508,760 (Olson et al.) discloses encapsulation of electroluminescent phosphors via vacuum deposition of certain polymers.

It is also known to encapsulate phosphor particles in inorganic coatings, e.g., oxide coatings. U.S. Patent No. 3,264,133 (Brooks) discloses the deposition of coatings such as titania (TiO_2) on phosphor particles by washing the particles in a predominantly alcohol solution of a halogen-containing constituent, e.g., titanium tetrachloride, and then drying and firing the particles.

Vapor phase reaction and deposition processes have been used to coat phosphor particles with inorganic coatings. Such techniques are typically considered as superior in providing more complete, uniform, and defect-free coatings. Phosphor particles encapsulated with such techniques have exhibited substantial resistance to humidity-accelerated decay. However, significant reductions in humidity-accelerated decay of luminescent brightness have been obtained only in conjunction with greatly diminished initial luminescent brightness and in some instances, undesirable color shift of the light emitted by the encapsulated phosphor particles.

For instance, U.S. Patent No. 4,855,189 (Simopoulous et al.) discloses encapsulation of phosphor particles with SiO_2 via a chemical vapor deposition process ("CVD") wherein phosphor particles are subjected to a temperature of about 490°C and an atmosphere of oxygen and silane gas while being agitated. Phosphor particles encapsulated in accordance with this reference have been found to exhibit a substantial reduction in initial electroluminescent brightness for given excitement conditions.

Air Force Technical Report AFFDL-TR-68-103 (Thompson et al., July 1968) discloses vapor phase encapsulation of electroluminescent phosphor particles for the purpose of attempting to improve performance at elevated temperatures. That reference discloses use of a fluidized bed chemical vapor deposition ("CVD") process to deposit several different oxide coatings onto zinc sulfide-based phosphors. Oxide coatings were deposited from a variety of precursor materials at furnace settings of about 200°C to about 500°C . The reactor temperature profile was such that the maximum temperature within the reaction zone was typically 100°C higher than the nominal temperature setting, accordingly, the maximum temperatures within the reactor ranged upward of about 300°C for the various deposition runs disclosed therein. Titania-coated zinc sulfide/zinc selenide phosphors were found to have a reduced humidity-accelerated decay, but the initial luminescent brightness of the encapsulated phosphors was only about 25 percent that of the original material in uncoated form.

EP-A-0 160 856 also discloses encapsulation of phosphor particles by a chemical vapor deposition process. Phosphor particles suspended in a fluidized bed are exposed to vaporized coating precursor material at a first temperature (which is less than the temperature at which the precursor material decomposes) and then the precursor-enveloped particles are heated to a second temperature at which the precursor material reacts to form the final coating. The temperature gradient maintained in the reaction furnace typically ranged from about 60 to 150°C at the frit area to above 450°C at the area beyond the oxidizing gas inlet where reaction of the precursor material occurs.

The prior art does not disclose a technique for encapsulating phosphor particles that provides desired moisture-resistance coupled with high levels of initial luminescent brightness relative to the initial luminescent brightness of the uncoated phosphor particles.

Summary of Invention

The present invention provides novel encapsulated phosphor particles having thin, substantially transparent metal oxide coatings which exhibit unexpectedly high initial luminescent brightness coupled with surprising resistance to humidity-accelerated decay of luminescent brightness.

The present invention also relates to a novel method for making such encapsulated phosphor particles utilizing relatively low temperature vapor phase hydrolysis reactions and deposition processes.

Briefly summarizing, encapsulated phosphor particles of the invention each comprise a particle of zinc sulfide-based luminescent phosphor which is essentially completely encapsulated within a substantially transparent, continuous metal oxide coating. In accordance with the invention, the encapsulated particle has an electroluminescent brightness which is equal to or greater than 50 percent of the luminescent brightness of the original uncoated phosphor particle when excited in the same manner. Further, encapsulated phosphor particles of the invention exhibit substantially reduced humidity-accelerated brightness decay, i.e., their brightness decay characteristics in operating conditions of 95 percent or more relative humidity are substantially the same as their intrinsic decay characteristics, such that the percent of electroluminescent brightness retained following 100 hours of operation in an environment having a relative humidity of at least 95 percent is greater than about 70 percent, preferably greater than about 80 percent, and most preferably greater than about 90 percent, of the intrinsic brightness of the encapsulated phosphor particles retained following 100 hours operation under substantially the same operating conditions of temperature, and voltage and frequency of applied electric field. Intrinsic brightness of the encapsulated phosphor particles refers to the electroluminescent brightness of such particles when operated under a relative humidity of less than 10 percent.

In brief summary, the novel method of the invention comprises:

- a) providing an agitated bed of phosphor particles;

- b) heating the bed to a temperature of between about 25°C and about 170°C;
 c) exposing the bed to one or more vapor phase oxide precursors such that the precursors chemically react and form hermetic, substantially transparent metal oxide coatings on the surfaces of the particles, thereby yielding essentially encapsulated phosphor particles; and
 d) cooling the resultant encapsulated particles.

The initial electroluminescent brightness of encapsulated phosphor particles of the invention is typically at least about 50 percent of the initial luminescent brightness of the phosphor particles in their initial uncoated state, preferably at least about 70 percent of that initial brightness, and most preferably at least about 80 percent of that initial brightness. The brightness decay during operation while exposed to high humidity, e.g., relative humidity of over 80 percent, is much less than that of the uncoated phosphor under the same conditions, and is typically substantially the same as the intrinsic decay of the subject phosphor. Phosphor particles of the invention provide a surprising combination of high initial electroluminescent brightness and humidity resistance, a combination which was heretofore unavailable.

Brief Description of Drawing

The invention will be further explained with reference to the drawing, wherein:

Figure 1 is a schematic illustration of one embodiment of the method for making encapsulated phosphor particles in accordance with the present invention;

Figure 2 is a cross-sectional illustration of phosphor particles of the invention; and

Figures 3 and 4 are graphical illustrations of the decay characteristics of illustrative encapsulated phosphor particles of the invention and the decay characteristics of uncoated phosphor particles of the same composition.

These figures are idealized and are intended to be merely illustrative and non-limiting.

Detailed Description of Illustrative Embodiments

Phosphor particles used in the invention comprise zinc sulfide-based electroluminescent materials. Such phosphors are well-known and commonly include one or more of such compounds as copper sulfide (CuS), zinc selenide (ZnSe), and cadmium sulfide (CdS) in solid solution within the zinc sulfide crystal structure or as second phases or domains within the particle structure.

Phosphors commonly contain moderate amounts of other materials such as dopants, e.g., bromine, chlorine, manganese, silver, etc., as color centers, as activators, or to modify defects in the particle lattice to modify properties of the phosphor as desired. Phosphors used in the present invention may be formulated in accordance with conventional practices.

Good results have been obtained with several commercially available phosphors including Sylvania Type 723, 728, and 830 Phosphors. Sylvania Type 723 is believed to be a copper-activated zinc sulfide phosphor which provides green fluorescence under an applied electric field. Sylvania Type 728 is believed to be a copper-activated zinc sulfide phosphor which provides green fluorescence under an applied electric field. Sylvania Type 830 is believed to be a blend of copper/manganese-activated zinc sulfide and copper-activated zinc sulfide which provides a white fluorescence under an applied electric field.

Phosphor particles used herein may be of many sizes, typically depending to large extent on the particular application. Phosphor particles having average particle diameters of between about 1 and about 50 microns, preferably between about 10 and 40 microns, are typically useful for screen printed and roll coated panels, for CRT screens, light bulbs, as well as many other applications. Phosphor particles which are too large may interfere with formation of very thin phosphor layers, may result in grainy or nonuniform light output, and typically tend to settle too quickly from suspensions during device fabrication. Phosphor particles which are too small may tend to degrade more rapidly during use due to increased relative surface area, may tend to agglomerate so as to interfere with free flow characteristics, and may be difficult to mix with binders in desirably high loadings.

Encapsulated phosphor particles of the invention are essentially completely coated with a substantially continuous coating of one or more oxides. As used herein, "metal oxide coating" means a material made up primarily of metal cations and oxygen, but which may contain minor amounts of other elements and compounds originating in the precursor materials or phosphor particles, which can be generated in coating form on phosphor particles under the conditions described herein. Advantageous results have been obtained with coatings of titania (TiO₂) and titania/silica TiO₂/(SiO₂). It is believed that useful results may also be obtained with other oxides formed from precursors in low temperature reactions such as silica (SiO₂), alumina (Al₂O₃), tin oxide (SnO₂), zirconia (ZrO₂), etc., and similarly formed compound oxides such as mullite (3Al₂O₃ · 2SiO₂).

The metal oxide coating is substantially transparent and is typically between about 0.1 and 3.0 microns thick, preferably between about 0.1 and about 0.5 microns thick. Coatings which are too thin may tend to provide insufficient impermeability to moisture. Coatings which are too thick may tend to be less transparent and result in reduced brightness.

As mentioned above, the novel method of the invention comprises:


- a) providing an agitated bed of phosphor particles;
- b) heating the bed to a temperature of between about 25°C and about 170°C, preferably between about 100°C and about 150°C;
- c) exposing the bed to one or more vapor phase oxide precursors such that the precursors chemically react to form oxides in the presence of the phosphor particles and deposit on the surfaces of the phosphor particles an essentially continuous, substantially transparent oxide coating, thereby yielding essentially encapsulated phosphor particles; and
- d) cooling the resultant encapsulated particles. An illustrative embodiment of the novel process of the invention is shown schematically in Figure 1.

During manufacture, phosphor particles may typically be washed to remove residual amounts of dopants left on the surfaces thereof, e.g., copper sulfide may be removed with a potassium cyanide solution. Generally, commercially available phosphor particles are suitable for use in the present invention in the condition supplied by the manufacturer without any further special surface preparation.

Uncoated phosphor particles 12 are placed in reactor 14 and heated to between about 25°C and about 170°C, preferably between about 100°C and 150°C. In order to form substantially continuous coatings covering essentially the entire surfaces of the phosphor particles, the particles are preferably agitated while in the reaction chamber. Illustrative examples of useful methods for agitating the phosphor particles include shaking, vibrating, or rotating the reactor, stirring the particles, or suspending them in a fluidized bed. In such reaction chambers, the particles may be agitated by many different ways such that essentially the entire surface of each particle is exposed and the particles and reaction precursors may be well intermixed. Typically, a preferred reaction chamber is a fluidized bed reactor. Fluidizing typically tends to effectively prevent agglomeration of the particles, achieve uniform mixing of the particles and reaction precursor materials, and provide more uniform reaction conditions, thereby resulting in highly uniform encapsulation characteristics.

Although not required in many instances, it may be desired when using phosphor particles which tend to agglomerate to add fluidizing aids, e.g., small amounts of fumed silica. Selection of such aids and of useful amounts thereof may be readily determined by those with ordinary skill in the art.

Precursor materials in vapor phase are then added to the reactor. The present invention utilizes a vapor phase hydrolysis reaction to form a coating of oxide material on the surfaces of the phosphor particles thereby encapsulating them. Such process is sometimes referred to as a chemical vapor deposition ("CVD") reaction. The following is an illustrative reaction:



In the illustration, water vapor and titanium tetrachloride are considered oxide precursor materials.

One technique for getting the precursor materials into vapor phase and adding them to the reaction chamber is to bubble a stream of gas, preferably inert, referred to herein as a carrier gas, through a solution or neat liquid of the precursor material and then into the reaction chamber. Illustrative examples of inert gases which may be used herein include argon and nitrogen. Oxygen and/or air may also be used. An advantage of this technique is that the carrier gas/precursor streams may be used to fluidize the phosphor particles in the reaction chamber, thereby facilitating the desired encapsulation process. In addition, such a technique provides means for readily controlling the rate of introduction of the precursor materials into the reactor. Referring again to Figure 1, carrier gas 2 is bubbled through water bubbler 4, to produce water vapor-containing precursor stream 8, and carrier gas 2 is also bubbled through titanium tetrachloride bubbler 6, to produce titanium tetrachloride-containing precursor stream 10. Precursor streams 8 and 10 are then transported into reactor 14.

Precursor flow rates are adjusted to provide an adequate deposition rate and to provide an oxide coating of desired quality and character. Flow rates are adjusted such that the ratios of precursor materials present in the reactor chamber promote oxide deposition at the surface of the phosphor particles substantially without formation of discrete, i.e., free floating, oxide particles, elsewhere in the chamber. For example, when depositing coatings of titania from titanium tetrachloride and water, a high ratio of tetrachloride molecules to water molecules is maintained such that most of the available water in the reaction chamber remains absorbed on the surfaces of the phosphor particles and little is in free state elsewhere in the chamber. Such a ratio is also believed to promote the formation of more anhydrous titania films

which are believed to provide optimum protection against humidity-accelerated decay.

Optimum flow rates for a particular application typically depend in part upon the temperature within the reaction chamber, the temperature of the precursor streams, the degree of particle agitation within the chamber, and the particular precursors being used, but useful flow rates may be readily determined with trial and error. In preferred embodiments, the flow rate of carrier gas used to transport the precursor materials to the reaction chamber is sufficient to agitate the phosphor particles as desired and also transport optimal quantities of precursor materials to the chamber.

Preferably, the precursor materials have sufficiently high vapor pressures that sufficient quantities of precursor material will be transported into the reactor for the hydrolysis reaction and coating process to proceed at a conveniently fast rate. For instance, precursor materials having higher vapor pressures will typically provide faster deposition rates than will precursor materials having lower vapor pressures, thereby enabling the use of shorter encapsulation times. Precursor sources may be heated to increase the vapor pressure of the material, however, this may necessitate heating of tubing or other means used to transport the precursor material to the reactor so as to prevent condensation between the source and the reactor. In many instances, precursor materials will be in the form of neat liquids at room temperature. In some instances, the precursor materials may be available as sublimable solids.

Precursor materials that are capable of forming hermetic oxide coatings via hydrolysis reactions at low temperatures, e.g., below about 170°C and preferably below about 150°C, are preferred. Advantageous results have been obtained with titanium tetrachloride or silicon tetrachloride, and water as precursor materials. In addition to such metal chlorides, useful results are also expected with metal alkoxides, e.g., titanium isopropoxide, silicon ethoxide, and zirconium n-propoxide.

Preferably, the mutually reactive precursor materials, e.g., TiCl_4 and H_2O , are not mixed prior to being added to the reactor in order to prevent premature reaction within the transport system. Accordingly, multiple gas streams into the reactor chamber are typically provided.

The temperature of the reactor is maintained at between about 25°C and about 170°C, and preferably between about 100°C and about 150°C. It has been observed that encapsulation processes performed at temperatures within this range provide deposition of desired hermetic coatings that provide desired protection against humidity-accelerated decay while avoiding intrinsic thermal damage or adverse thermochemical reactions at the surfaces of the particles which cause undesirable loss of initial brightness. Encapsulation processes which are performed at temperatures which are too low may tend to result coatings which do not provide desired resistance to humidity-accelerated decay. Such coatings are not sufficiently moisture impermeable, a result it is believed of having a more open or more hydrated structure. Encapsulation processes which are performed at temperatures which are too high may result in decreased electroluminescent brightness, undesirable changes or shifts in the color of the light emitted by the subject phosphor, or degradation of the intrinsic decay characteristics of the subject phosphor material.

Although it has been suggested in the prior art that exposing phosphor particles to high temperatures, e.g., above about 350°C, tends to reduce the initial luminescent brightness thereof, it has been found that phosphor particles may be degraded by exposure to lower temperatures, e.g., about 170 to about 200°C, under certain conditions. While I do not wish to be bound by this theory, it is postulated that phosphor materials are not sensitive only to the temperatures to which they are exposed, but that one or more effects caused by exposure of the particles to certain compositions, e.g., exposure to certain compounds, also exist, and that such effects are also dependent upon temperature. A specific mechanism is not yet determined, but it is believed that the surface of the phosphor particles may undergo some change by exposure to such agents as hydrochloric acid such as is generated during vapor generation and deposition of titania coatings from titanium tetrachloride which affects the luminescent brightness of the resultant encapsulated particle.

Accordingly, encapsulation of phosphor particles as described herein is preferably performed at temperatures between about 25°C and about 170°C, preferably between about 100°C and about 150°C. Referring again to Figure 1, following encapsulation, encapsulated phosphor particles 16 of the invention are removed from reactor 14. As illustrated in Figure 2, typically encapsulated phosphor particles 20 of the invention consist essentially of particle 22 of phosphor material which is essentially completely encapsulated within substantially transparent, continuous oxide coating 24.

Encapsulated phosphor particles of the invention provide both high resistance to humidity-accelerated decay and substantially retain their intrinsic properties. For instance, there is typically little or no shift in the emission spectra of phosphor particles encapsulated as taught herein, such particles typically retain a substantial portion of their initial luminescent brightness, and the intrinsic decay characteristics are typically similar to or even better than those of the uncoated phosphor particles.

The resistance to humidity-accelerated decay is typically such that the rate of brightness loss when operated while directly exposed to high humidity, e.g., a relative humidity of greater than 95 percent, is substantially no greater than the intrinsic brightness loss exhibited during operation in a dry environment, e.g., a relative humidity of less than about 10 percent. In an illustrative example, the luminescent brightness of an encapsulated phosphor of the invention, after operation for 100 hours in an environment having a relative humidity of at least 95 percent, was over 90 percent of the

luminescent brightness of similarly encapsulated phosphor particles after operation for 100 hours in an environment having a relative humidity of less than 10 percent.

Figure 3 is a graphical illustration of the relative absolute electroluminescent brightness versus time of operation of illustrative encapsulated phosphor particles of the invention and the same phosphor material in uncoated state. In Figure 3, the difference in position on the Y (vertical) axis is proportional to the difference in absolute brightness of the subject phosphors. Each curve was derived from the average of several samples of the indicated type. Curve 50 represents the decay characteristics of uncoated phosphor material operated in a dry environment (relative humidity less than 10 percent) and Curve 52 represents the decay characteristics of uncoated phosphor material operated in a high humidity environment (relative humidity over 95 percent). The substantial difference between Curve 50 and Curve 52 represents humidity-accelerated brightness decay of the uncoated phosphor material. Curve 60 represents the decay characteristics of encapsulated phosphor particles of the same phosphor material, encapsulated in accordance with the invention, operated in the same dry environment. Curve 62 represents the decay characteristics of encapsulated phosphor particles of the same phosphor material, encapsulated in accordance with the invention, operated in the same humid environment described above. The small differential between Curves 60 and 62 indicates that humidity-accelerated brightness decay has been substantially eliminated by encapsulation in accordance with the present invention. Curves 60 and 62 begin at lower absolute brightness, representing the reduction in initial electroluminescent brightness (about 75 percent of that of the uncoated phosphor material) resulting from the encapsulation process. Such performance is substantially better than that achieved with previously known encapsulation techniques. For instance, phosphor particles encapsulated in accordance with U.S. Patent No. 4,855,189 have been found to have an initial brightness of only about 30 percent of that of the uncoated phosphor.

Figure 4 is a graphical illustration of the percent of retained luminescent brightness of each of the subject phosphors versus time of operation of encapsulated phosphor particles of the invention and the same phosphor material in an uncoated state. Each curve was derived from the average of several of samples of the indicated type. Curve 54 represents the decay characteristics of uncoated phosphor material operated in a dry environment (relative humidity less than 10 percent) and Curve 56 represents the decay characteristics of uncoated phosphor material operated in a high humidity environment (relative humidity over 95 percent). Curve 64 represents the decay characteristics of encapsulated phosphor particles of the same phosphor material, encapsulated in accordance with the invention, operated in the same dry environment. Curve 66 represents the decay characteristics of encapsulated phosphor particles of the same phosphor material, encapsulated in accordance with the invention, operated in the same humid environment.

In accordance with the present invention, encapsulated phosphor particles may be made which exhibit the exceptional resistance to humidity-accelerated decay described above and also provide high initial electroluminescent brightness. For instance, encapsulated phosphor particles of the invention can be made with Sylvania Type 723 Phosphor which exhibit an initial electroluminescent brightness of at least about 51.4 cd/m² (15 foot-Lamberts), preferably at least about 68.5 cd/m² (20 foot-Lamberts), most preferably at least about 78.8 cd/m² (23 foot-Lamberts), as measured by providing a 100 micron thick layer of the encapsulated phosphor particles in dielectric oil (castor oil) with an ITO on glass electrode (transmission about 90 percent) that had been sprayed with substantially transparent acrylic coating about 1000 angstroms thick thereover, the layer containing 66 weight percent of phosphor particles, applying an electric field having a voltage of about 600 volts and a frequency of about 500 Hertz, and measuring the magnitude of light emitted through the electrode. In an uncoated state, Sylvania Type 723 Phosphor was found to exhibit an initial electroluminescent brightness of 101.1 cd/m² (29.5 foot-Lamberts). In an uncoated state, Sylvania Type 728 Phosphor has been found to exhibit an initial electroluminescent brightness of about 107.9 cd/m² (31.5 foot-Lamberts), and encapsulated phosphor particles of the invention having brightness of at least about 54.8 (16), preferably 75.4 (22), and most preferably 85.6 cd/m² (25) (foot-Lamberts) can be made therewith. In an uncoated state, Sylvania Type 830 Phosphor has been found to exhibit an initial electroluminescent brightness of about 37.7 cd/m² (11 foot-Lamberts), and encapsulated phosphor particles of the invention having brightnesses of at least about 20.6 (6), preferably 27.4 (8), and most preferably 30.8 cd/m² (9) (foot-Lamberts) can be made therewith.

Examples

The invention will be further explained by the following illustrative examples which are intended to be nonlimiting. Unless otherwise indicated, all amounts are expressed in parts by weight. Flow rates refer to the metered volume of carrier gas (nitrogen gas) through the indicated solutions.

Encapsulation Process

Fluidized bed reactors consisting of glass-frit type funnels with a single bottom inlet and size D frit were used. As indicated below, 20 millimeter and 40 millimeter reactors modified for oil bath immersion or for heating with nichrome wire were used. The 20 millimeter reactors were used with a single gas inlet tube and the 40 millimeter reactors with

two gas inlet tubes. The gas inlet tubes were glass tubes, 10 millimeters in diameter, with size C glass frits which were inserted into the fluidized bed extending from the top of the funnel to introduce carrier gas and metal tetrachloride vapors into the reaction zone. A separate tube was connected to the bottom of the reactor and water vapor introduced into the reactor therethrough.

Bubbler sizes were about 300 milliliters for the 20 millimeter diameter reactors and 800 milliliters for the 40 millimeter diameter reactors.

Carrier gas and water vapor were passed through the funnel frit supporting the phosphor particles. Reagent grade neat liquids of titanium tetrachloride and silicon tetrachloride from Aldrich Chemical Company were used as indicated.

Brightness

The electroluminescent brightness of phosphor samples was determined in test cells comprising a machined aluminum grid with 100 micron spacing between electrodes. Each cell was filled with a mixture of phosphor particles and liquid dielectric oil, Dow Corning FS1265 fluorosilicon oil or castor oil, at about 66 weight percent particles. A transparent top electrode comprising a sheet of indium tin oxide coated polyester film (DX ITO/PE from Southwall Corporation), having about 90 percent transmission, was mounted over the top of the grid. Tests were run under an applied electric field of 220 volts, 400 Hertz, in sealed battery jars maintained with water-saturated air, i.e., relative humidity of above 95 percent, or desiccant, i.e., relative humidity of below 10 percent. Samples were run continuously for at least 96 hours.

Abbreviations

The following abbreviations are used in reporting the examples:

Abbrev.	Meaning
IB	Initial Brightness of phosphor sample at beginning of brightness test as percentage of initial luminescent brightness of same phosphor in fresh, uncoated condition.
RB	Retained Brightness of phosphor sample after about 96 hours continuous operation of brightness cell as percentage of Initial Brightness of same phosphor.
RH	Relative Humidity under which luminescent brightness was determined.
SEM	Scanning Electron Microscope.

Phosphor Specifications

Commercially available Sylvania type 723, 723RB, 728, and 830 Phosphors were used in the Examples as indicated. The physical properties of those phosphors are reported by the seller as follows:

Type	Size Distrib. ¹				Density ²		
	25%	50%	75%	SS ³	M	B	Color ⁴
723	22	28	35	22	4.1	1.94	Light green
728	24	31	38	23	4.1	1.94	Light green
830	22	28	35	22	4.1	1.94	Light tan

¹ Particle Size Distribution - Coulter Counter, size in micrometers at listed percentiles.

² Material ("M") and Bulk ("B") Density in grams/cubic centimeter.

³ Fisher Sub-Sieve Size.

⁴ Body color.

Type 723 RB Phosphor has been observed to exhibit a greater shift to blue emission when high frequency electric fields are applied, but is otherwise believed to be substantially similar to Type 723 Phosphor. Type 723RB Phosphor is reported to have the same physical properties as listed above for Type 723.

Example 1

A 20 millimeter diameter reactor heated with nichrome wire was used to encapsulate 20 grams of Sylvania Type 723 Phosphor with titania.

During encapsulation the temperature was maintained at $137^{\circ}\text{C} \pm 8^{\circ}\text{C}$. The flow rates of dry nitrogen through the

water and titanium bubblers were 100 centimeters³/minute and 260 centimeters³/minute, respectively. The encapsulation process was run for 4 hours. Small samples were removed from the reactor every hour and immersed in 0.1 molar silver nitrate solution and observed. The uncoated phosphor turned black within a few minutes as silver sulfide formed at the surface of the particles. Phosphor particles removed after 1 hour turned gray, indicating incompletely encapsulated particles. Phosphor particles removed after 2 or more hours were unaffected by the solution, indicating that they were essentially completely encapsulated with a coating which was impermeable to the solution. Negligible change in coloration of the immersed particles was observed over a period of several weeks.

SEM analysis revealed that the phosphor particles had coating thicknesses of between 0.2 and 0.4 microns. The coatings appeared to completely cover the surfaces of the particles and no pores were visible.

Brightness results of the encapsulated phosphor particles, identified as Sample 1, are tabulated in Table I below. The corresponding results for untreated phosphor particles, identified as sample A are also listed for comparison.

Table I

Sample	RH	IB	RB
A	<10	100	75
A	>95	100	0
1	<10	77	88
1	>95	77	88

The Retained Brightness of Sample A differed markedly between operation in humid conditions and operation in dry conditions. However, in Sample 1 it was substantially the same, indicating high resistance to humidity-accelerated decay. In other tests, operation of encapsulated phosphor particles of the invention in humid environments was found to have resulted in a somewhat lower Retained Brightness than operation in dry environments, but in all instances the differential was small and high resistance to humidity-accelerated decay was obtained.

Examples 2-7

Several 20 gram batches of Sylvania No. 723 Phosphor were coated with titania as in Example 1, except the average temperature and flow rates were varied as indicated. The reaction conditions and brightness properties of the resultant encapsulated phosphor particles are tabulated in Table II.

Table II

Sample	Temp ¹	Water ²	TiCl ₄ ³	IB	RB
2	130	100	220	77	85
3	140	100	220	73	82
4	150	100	220	69	59
5	140	200	120	72	18
6	140	170	120	68	56
7	140	120	200	73	86

¹ Average reaction temperature in °C.

² Flow rate through water bubbler in centimeters³/minute.

³ Flow rate through TiCl₄ bubbler in centimeters³/minute.

Examples 2-4 illustrate a tendency toward reduced initial luminescent brightness with increasing reaction temperature, indicating that minimization of reaction temperature below certain levels is important for maintaining high initial luminescent brightness.

Examples 5-7 illustrate a tendency toward increased retention of luminescent brightness with higher ratios of titanium tetrachloride to water precursor flows. This effect may have been observed because the resultant coatings made with lower ratios were less anhydrous or because the limited amount of available titanium tetrachloride resulted in slower reaction and thinner resultant coating, which in thicker form might have provided better resistance to humidity-accelerated decay.

Examples 8-10

Several batches of Sylvania No. 723 Phosphor were encapsulated as in Example 1 except (1) an oil bath was used to maintain an average reaction temperature of about $140^{\circ}\text{C} \pm 5^{\circ}\text{C}$ and (2) the chloride bubbler contained a mixture of titanium tetrachloride and silicon tetrachloride in the indicated volume ratio. The flow rate through the water bubbler was 100 centimeters³/minute and the flow rate through the chloride bubbler was 220 centimeters³/minute.

Table III

Sample	Ratio	IB	RB
8	40/60	82	89
9	60/40	87	88
10	80/20	80	83

Examples 11-15

Several batches of Sylvania No. 723 Phosphor were encapsulated as in Example 1 except that a 40 millimeter diameter reactor and 100 grams or 200 grams as indicated of phosphor were used, and the reaction was continued for the indicated time. Nitrogen flow rates through the water and titanium tetrachloride bubblers were 1300 cubic centimeters/minute and 350 cubic centimeters/minute, respectively.

Table IV

Sample	Temp ¹	Amount ²	Time ³	IB
11	200	200	9	14
12	187	100	7	22
13	170	100	5	32
14	157	100	5	60
15	150	100	5	67

¹ Average reaction temperature in $^{\circ}\text{C}$.

² Amount of phosphor in charge.

³ Length of reaction time.

Examples 11-15 illustrate a tendency toward reduced initial luminescent brightness with increasing reaction temperature, indicating that minimization of reaction temperature below certain levels is important for maintaining high initial luminescent brightness.

Examples 16-25

Several 150 gram batches of Sylvania No. 723 Phosphor were encapsulated with titania using a 40 millimeter diameter reactor with 2 top gas inlets for oxide precursors. The temperature was controlled to $\pm 2^{\circ}\text{C}$ of the indicated value using an oil bath.

Table V

Sample	Temp ¹	A Flow ²	B Flow ³	Water ⁴	Time ⁵	IB	RB
16	135	600	600	600	5.5	77	87
17	135	600	600	600	6.0	74	82
18	138	640	600	310	7.5	75	77
19	138	640	600	350	7.5	77	73
20	138	640	600	450	8.5	72	81
21	128	640	600	450	7.5	71	80
22	128	640	600	450	8.0	69	83
23	128	640	600	480	8.0	72	88
24	138	680	700	550	4.0	84	81
25	138	680	700	600	4.0	79	88

¹ Reaction temperature in °C.² Flow rate through TiCl₄ bubbler A in centimeters³/minute.³ Flow rate through TiCl₄ bubbler B in centimeters³/minute.⁴ Flow rate through water bubbler in centimeters³/minute.⁵ Reaction time in hours.Examples 26-28

Three 20 gram batches of encapsulated phosphor particles were made using Sylvania No. 723, 728, and 830 Phosphor, respectively. In each case the phosphor particles were encapsulated using a 20 millimeter diameter reactor heated in an oil bath to an average temperature of about 128°C. The encapsulation reaction was run for 3.5 hours at the indicated flow rates.

Table VI

Sample	Phosphor	TiCl ₄ ¹	Water ²	IB	RB
26	723RB	200	105	72	83
27	728	220	110	68	83
28	830	220	110	84	81

¹ Flow rate through TiCl₄ bubbler in centimeters³/minute.² Flow rate through water bubbler in centimeters³/minute.

Various modifications and alterations of this invention will become apparent to those skilled in the art.

Claims

1. Encapsulated electroluminescent phosphor particles, characterized in that each comprises a particle of zinc sulfide-based electroluminescent phosphor which is essentially completely encapsulated within a substantially transparent, continuous metal oxide coating;

wherein said encapsulated phosphor particles have an initial electroluminescent brightness which is equal to or greater than about 50 percent of the initial electroluminescent brightness of the uncoated phosphor particles, and wherein the percent of luminescent brightness retained following 100 hours operation in an environment having a relative humidity of at least 95 percent is greater than about 70 percent of the intrinsic brightness retained following 100 hours operation, wherein change in electroluminescent brightness in an environment having a relative humidity of at least 95 percent and intrinsic brightness change are measured under substantially equivalent operating conditions of temperature, voltage, and frequency.

2. The encapsulated phosphor particles of claim 1 further characterized in at least one of the following:

a) the initial electroluminescent brightness of said particles is equal to or greater than about 70 percent of the initial luminescent brightness of the uncoated phosphor particles; or

b) the initial electroluminescent brightness of said particles is equal to or greater than about 80 percent of the initial luminescent brightness of the uncoated phosphor particles.

3. The encapsulated phosphor particles of claim 1 further characterized in at least one of the following:

- a) said retained electroluminescent brightness is greater than about 80 percent of said intrinsic brightness; or
- b) said retained electroluminescent brightness is greater than about 90 percent of said intrinsic brightness.

4. The encapsulated phosphor particles of claim 1 further characterized in at least one of the following:

- a) said particles comprise zinc sulfide-based phosphor materials and contain minor amounts of one or more of the following: cadmium, selenium, copper, bromine, chlorine, manganese, or silver; or
- b) said particles are between about 1 and about 50 microns in diameter; or
- d) said particles are between about 10 and about 40 microns in diameter.

5. The encapsulated phosphor particles of claim 1 further characterized in at least one of the following:

- a) said coating is between about 0.1 and about 3.0 microns thick; or
- b) said coating is between about 0.1 and about 0.5 microns thick; or
- c) said coating comprises at least one of the following: titania, silica, alumina, tin oxide, zirconia, or mullite.

6. The encapsulated electroluminescent phosphor particles of claim 1, wherein the initial brightness, change in electroluminescent brightness in an environment having a relative humidity of at least 95 percent, and intrinsic brightness change are measured at ambient temperature under an applied electric field of 2.20 volts per micron and a frequency of 400 Hertz.

7. An electroluminescent device comprising a layer of a dielectric matrix loaded with the phosphor particles of claim 1, said layer being coated on a substrate having a front electrode, said device further having a rear electrode on the back side of said layer.

8. A process for encapsulating phosphor particles in substantially transparent metal oxide coatings said process characterized in that it comprises:

- a) providing an agitated bed of phosphor particles;
- b) heating said bed to a temperature of between about 25°C and about 170°C;
- c) exposing said bed to one or more vapor phase oxide precursors such that said precursors chemically react and form hermetic, substantially transparent metal oxide coatings on the surfaces of said particles, thereby yielding essentially encapsulated phosphor particles; and
- d) cooling said encapsulated particles.

9. The process of claim 8 further characterized in that said bed is heated to a temperature of between about 100°C and about 150°C.

10. The process of claim 8 further characterized in at least one of the following:

- a) said vapor phase oxide precursors comprise water vapor, titanium tetrachloride, and silicon tetrachloride; or
- b) said vapor phase oxide precursors comprise water vapor and one or more metal alkoxides or metal chlorides.

11. The process of claim 8 further characterized in at least one of the following:

- a) said phosphor particles comprise zinc sulfide-based phosphor materials; or
- b) said particles comprise zinc sulfide-based phosphor materials and contain minor amounts of one or more of the following: cadmium, selenium, copper, bromine, chlorine, manganese, or silver.

12. The process of claim 8 further characterized in at least one of the following:

- a) said phosphor particles are between about 1 and about 50 microns in diameter; or
- b) said phosphor particles are between about 10 and about 40 microns in diameter; or

- c) said oxide coatings are between about 0.1 and about 3.0 microns thick; or
 d) said oxide coatings are between about 0.1 and about 0.5 microns thick.

5 Patentansprüche

1. Gekapselte Elektrolumineszenz-Leuchtstoffpartikel, dadurch gekennzeichnet, daß jedes Partikel einen Elektrolumineszenz-Leuchtstoff auf der Basis von Zinksulfid aufweist, der im wesentlichen vollständig mit einer weitgehend transparenten, zusammenhängenden Metalloxid-Beschichtung gekapselt ist; welche gekapselte Leuchtstoffpartikel eine Anfangs-Leuchtdichte der Elektrolumineszenz haben, die gleich oder größer ist als etwa 50 % der Anfangs-Leuchtdichte der Elektrolumineszenz der nichtbeschichteten Leuchtstoffpartikel, und bei welchen gekapselten Leuchtstoffpartikeln die relative Leuchtdichte der Elektrolumineszenz, die nach einem Betrieb von 100 Stunden in einer Umgebung mit einer relativen Luftfeuchtigkeit von mindestens 95 % bewahrt bleibt, größer ist als etwa 70 % der nach einem Betrieb von 100 Stunden verbleibenden Eigenleuchtdichte und bei welchen gekapselten Leuchtstoffpartikeln die Änderung der Leuchtdichte der Elektrolumineszenz in einer Umgebung mit einer relativen Feuchtigkeit von mindestens 95 % und der Eigenleuchtdichte unter im wesentlichen gleichwertigen Betriebsbedingungen von Temperatur, Spannung und Frequenz gemessen werden.
2. Gekapselte Leuchtstoffpartikel nach Anspruch 1, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
 - a) die Anfangs-Leuchtdichte der Elektrolumineszenz der Partikel ist gleich oder größer als etwa 70 % der Anfangs-Leuchtdichte der nichtbeschichteten Leuchtstoffpartikel; oder
 - b) die Anfangs-Leuchtdichte der Elektrolumineszenz der Partikel ist gleich oder größer als etwa 80 % der Eigenleuchtdichte der nichtbeschichteten Leuchtstoffpartikel.
3. Gekapselte Leuchtstoffpartikel nach Anspruch 1, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
 - a) die verbleibende Leuchtdichte der Elektrolumineszenz ist größer als etwa 80 % der Eigenleuchtdichte; oder
 - b) die verbleibende Leuchtdichte der Elektrolumineszenz ist größer als etwa 90 % der Eigenleuchtdichte.
4. Gekapselte Leuchtstoffpartikel nach Anspruch 1, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
 - a) die Partikel umfassen Leuchtstoffmaterialien auf der Basis von Zinksulfid und enthalten geringfügige Menge von einem oder mehreren der folgenden: Cadmium, Selen, Kupfer, Brom, Chlor, Mangan oder Silber; oder
 - b) die Partikel haben einen Durchmesser zwischen etwa 1 und etwa 50 Mikrometer; oder
 - c) die Partikel haben einen Durchmesser zwischen etwa 10 und etwa 40 Mikrometer.
5. Gekapselte Leuchtstoffpartikel nach Anspruch 1, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
 - a) die Beschichtung hat eine Dicke zwischen etwa 0,1 und etwa 3,0 Mikrometer; oder
 - b) die Beschichtung hat eine Dicke zwischen etwa 0,1 und 0,5 Mikrometer; oder
 - c) die Beschichtung umfaßt mindestens eines der folgenden: Titandioxid, Siliciumdioxid, Aluminiumoxid, Zinn-oxid, Zirkoniumoxid oder Mullit.
6. Gekapselte Elektrolumineszenz-Leuchtstoffpartikel nach Anspruch 1, bei welchen die Anfangs-Leuchtdichte, die Änderung der Leuchtdichte der Elektrolumineszenz in einer Umgebung mit einer relativen Luftfeuchtigkeit von mindestens 95 % und die Änderung der Eigenleuchtdichte bei Außentemperatur mit einem angelegten elektrischen Feld von 2,20 Volt pro Mikrometer und einer Frequenz von 400 Hertz gemessen werden.
7. Elektrolumineszenz-Vorrichtung, umfassend eine Schicht einer dielektrischen Matrix, gefüllt mit den Leuchtstoffpartikeln nach Anspruch 1, wobei die Schicht auf einem Substrat mit einer vorderseitigen Elektrode aufgetragen ist, welche Vorrichtung ferner eine rückseitige Elektrode auf der Rückseite dieser Schicht aufweist.
8. Verfahren zum Verkapseln von Leuchtstoffpartikeln in weitgehend transparenten Metalloxid-Beschichtungen, wel-

ches Verfahren gekennzeichnet ist durch die Schritte:

- a) Bereitstellen eines Wirbelbettes von Leuchtstoffpartikeln;
 - b) Erhitzen des Bettes auf eine Temperatur zwischen etwa 25 °C und etwa 170 °C;
 - 5 c) Exponieren des Bettes an einer oder mehreren Dampfphasen-Oxidpräkursoren derart, daß die Präkursoren chemisch reagieren und auf den Oberflächen der Partikel hermetische und weitgehend transparente Metall-oxid-Beschichtungen bilden, wodurch weitgehend gekapselte Leuchtstoffpartikel erhalten werden; sowie
 - d) Kühlen der gekapselten Partikel.
- 10 9. Verfahren nach Anspruch 8, ferner dadurch gekennzeichnet, daß das Bett auf eine Temperaturen zwischen etwa 100 °C und etwa 150 °C erhitzt wird.
10. Verfahren nach Anspruch 8, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
- 15 a) die Dampfphasen-Oxidpräkursoren umfassen Wasserdampf, Titan-tetrachlorid und Siliciumtetrachlorid; oder
 - b) die Dampfphasen-Oxidpräkursoren umfassen Wasserdampf und ein oder mehrere Metallaloxide oder Metallchloride.
- 20 11. Verfahren nach Anspruch 8, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
- a) die Leuchtstoffpartikel umfassen Leuchtstoffmaterialien auf der Basis von Zinksulfid; oder
 - b) die Partikel umfassen Leuchtstoffmaterialien auf der Basis von Zinksulfid und enthalten geringfügige Mengen eines oder mehrerer der folgenden: Cadmium, Selen, Kupfer, Brom, Chlor, Mangan oder Silber.
- 25 12. Verfahren nach Anspruch 8, ferner gekennzeichnet durch mindestens eines der folgenden Merkmale:
- a) die Leuchtstoffpartikel haben einen Durchmesser zwischen etwa 1 und etwa 50 Mikrometer; oder
 - b) die Leuchtstoffpartikel haben einen Durchmesser zwischen etwa 10 und etwa 40 Mikrometer; oder
 - 30 c) die Oxid-Beschichtungen haben eine Dicke zwischen etwa 0,1 und etwa 3,0 Mikrometer; oder
 - d) die Oxid-Beschichtungen haben eine Dicke zwischen etwa 0,1 und etwa 0,5 Mikrometer.

Revendications

- 35 1. Particules de phosphore électroluminescent encapsulées, caractérisées en ce qu'elles comprennent chacune une particule de phosphore électroluminescent à base de sulfure de zinc qui est essentiellement totalement encapsulée à l'intérieur d'un revêtement d'oxyde métallique continu essentiellement transparent ;
- 40 en ce que lesdites particules de phosphore encapsulées ont une brillance électroluminescente initiale qui est égale ou supérieure à 50 % environ de la brillance électroluminescente initiale des particules de phosphore non-revêtues ; et en ce que le pourcentage de brillance électroluminescente préservée après 100 h d'opération dans un environnement ayant une humidité relative d'au moins 95 % est supérieur à 70 % environ de la brillance intrinsèque préservée après 100 h d'opération, la variation de brillance électroluminescente dans un environnement ayant une humidité relative d'au moins 95 % et la variation de brillance intrinsèque étant mesurées dans des
- 45 conditions opératoires essentiellement équivalentes de température, voltage et fréquence.
2. Particules de phosphore encapsulées suivant la revendication 1, caractérisée en outre par au moins une des conditions suivantes :
- 50 (a) la brillance électroluminescente initiale desdites particules est égale ou supérieure à 70 % environ de la brillance électroluminescente initiale des particules de phosphore non revêtues ; ou,
 - (b) la brillance électroluminescente initiale desdites particules est égale ou supérieure à 80 % environ de la brillance électroluminescente initiale des particules de phosphore non revêtues.
- 55 3. Particules de phosphore encapsulées suivant la revendication 1, caractérisée en outre par au moins une des conditions suivantes :
- (a) ladite brillance électroluminescente préservée est supérieure à 80 % environ de ladite brillance intrinsèque ;

ou,

(b) ladite brillance électroluminescente préservée est supérieure à 90 % environ de ladite brillance intrinsèque.

4. Particules de phosphore encapsulées suivant la revendication 1, caractérisée en outre par au moins une des conditions suivantes :

(a) lesdites particules comprennent des matériaux de phosphore à base de sulfure de zinc et contiennent des quantités mineures d'au moins un des éléments suivants cadmium, sélénium, cuivre, brome, chlore, manganèse ou argent ; ou,

(b) lesdites particules ont un diamètre compris entre environ 1 et environ 50 μm ; ou,

(c) lesdites particules ont un diamètre compris entre environ 10 et environ 40 μm .

5. Particules de phosphore encapsulées suivant la revendication 1, caractérisée en outre par au moins une des conditions suivantes :

(a) ledit revêtement a une épaisseur comprise entre environ 0,1 et environ 3,0 μm ; ou,

(b) ledit revêtement a une épaisseur comprise entre environ 0,1 et environ 0,5 μm ; ou,

(c) ledit revêtement comprend au moins un des éléments suivants : dioxyde de titane, silice, alumine, oxyde de zinc, zircone ou mullite.

6. Particules de phosphore électroluminescent encapsulées suivant la revendication 1, pour lesquelles la brillance initiale, la variation de brillance électroluminescente dans un environnement ayant une humidité relative d'au moins 95 % et la variation de brillance intrinsèque sont mesurées à la température ambiante sous un champ électrique de 2,20 V/ μm et une fréquence de 400 Hz.

7. Dispositif électroluminescent comprenant une couche d'une matrice diélectrique chargée de particules de phosphore suivant la revendication 1, ladite couche étant déposée sur un substrat ayant une électrode avant, ledit dispositif ayant en outre une électrode arrière sur le dos de ladite couche.

8. Procédé pour encapsuler des particules de phosphore dans des revêtements transparents d'oxyde métallique, ledit procédé étant caractérisé en ce qu'il comprend les étapes consistant à :

(a) faire appel à un lit agité de particules de phosphore ;

(b) chauffer ledit lit à une température se situant entre environ 25°C et 5 environ 170°C ;

(c) exposer ledit lit à un ou plusieurs précurseurs d'oxyde en phase vapeur de telle façon que lesdits précurseurs réagissent chimiquement et forment des revêtements hermétiques, essentiellement transparents d'oxyde métallique sur les surfaces desdites particules, pour conduire à des particules de phosphore essentiellement encapsulées ; et,

(d) refroidir lesdites particules encapsulées.

9. Procédé suivant la revendication 8, caractérisé en ce que ledit lit est chauffé à une température entre environ 100°C et 150°C.

10. Procédé suivant la revendication 8, caractérisé en outre par au moins une des conditions suivantes :

(a) lesdits précurseurs d'oxyde en phase vapeur comprennent la vapeur d'eau, le tétrachlorure de titane et le tétrachlorure de silicium ; ou,

(b) lesdits précurseurs d'oxyde en phase vapeur comprennent la vapeur d'eau et un ou plusieurs alkoxydes métalliques ou chlorures métalliques.

11. Procédé suivant la revendication 8, caractérisé en outre par au moins une des conditions suivantes :

(a) lesdites particules de phosphore comprennent des matériaux de phosphore à base de sulfure de zinc ; ou,

(b) lesdites particules de phosphore comprennent des matériaux de phosphore à base de sulfure de zinc ; et contiennent des quantités mineures de cadmium, sélénium, cuivre, brome, chlore, manganèse ou argent.

12. Procédé suivant la revendication 8, caractérisé en outre par au moins une des conditions suivantes :

- (a) lesdites particules de phosphore ont un diamètre compris entre environ 1 et environ 50 μm ; ou
- (b) lesdites particules de phosphore ont un diamètre compris entre environ 10 et environ 40 μm ; ou
- (c) lesdits revêtements d'oxyde ont une épaisseur comprise entre environ 0,1 et environ 3,0 μm ; ou
- (d) lesdits revêtements d'oxyde ont une épaisseur comprise entre environ 0,1 et environ 0,5 μm .

5

10

15

20

25

30

35

40

45

50

55




Fig. 1




Fig. 2




Fig. 3




Fig. 4

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.